

# Technical Data Sheet

**AkzoNobel**

Page 1/1

created on : 23.Feb.2018 ; Baek, HyungJun

This data sheet represents the actual status of the development and substitutes all previous.

TECHNICAL INFORMATION	
Name	RESOTHANE-HT#200(TX-F) TUS
Type	BTX-Free solvent-borne <input checked="" type="checkbox"/>
Color	METALLIC BLACK
Gloss	10.5 ± 0.5 (60° Geometry)
Supply viscosity	58.6 ± 3 KU (stomer , 25℃)
SG wet	0.96 ± 0.03 kg/ℓ
Weight solids	31.5 ± 2.0 %
Film thickness dry	20 ~ 25 μm DFT
Rec. coating system	Top Coat
Shelf life	9 months

The above data does not represent a specification

APPLICATION TIPS	
Before using	stir well
Substrate	ABS, PC+ABS
Pre treatment	Cleaning with IPA
Application method	Air assisted spraying
Thinner	A/T#570(TX-F) THINNER
Hardener	POLY HARD TX-F
Mixing ratio	100 / 16 / 40~60 w/w (Paint+Hardner+Thinner)
Application viscosity	13~15 sec (F/cup#4, 25℃)
Pot life	4 hrs
Flash off	10 mins × RT
Curing schedule	Over 30mins × 75 ± 5℃ Object temperature
Disposal	Do not allow into drains or watercourse

This information is based on tests and research carried out by ANICK.Ltd and was believed to be correct at the time this product sheet was printed but is subject to revision as additional knowledge and experience are gained. Neither ANICK nor any of its subsidiary or associated companies makes any guarantee as to results or otherwise assumes any liability or obligation whatsoever in connection with this information. This product sheet shall not create or form part of any contract between ANICK or any of its subsidiary or associated companies and any other person ; nor is it licence to operate under or intended to enable or induce infringement of any existing patent or other industrial property right.

AkzoNobel Industrial Coatings Korea.,Ltd. 11, Byeolmang-ro 459beon-gil, Danwon-gu, Ansan-si,  
Kyunggi-do, Korea. 425-833  
Tel : +82-31-363-4762, Fax : +82-31-363-4770

**AkzoNobel**