

## RESOTHANE-HT#200(TX-F) NNB(M)

Page 1/1

created on : 17. August. 2018 ; Park, JiHoon

### TECHNICAL INFORMATION

Type	: BTX-free solvent-borne	<input checked="" type="checkbox"/>
Color	: BLACK	
Gloss	: 2.2 ± 0.1 (60° Geometry)	
Supply viscosity	: 59 ± 3 KU (stomer, 25°C)	
SG wet	: 0.98 ± 0.03 kg/ℓ	
Weight solids	: 37.5 ± 2 %	
Film thickness dry	: 20 ~ 25 μm DFT	
Shelf life	: 9 months	
Rec. coating system	: One coat	

The above data does not represent a specification

### APPLICATION TIPS

Before using	: stir well
Substrate	: PC+ABS,ABS
Pre treatment	: Cleaning with IPA
Application method	: Air assisted spraying
Thinner	: A/T#570(TX-F) thinner
Hardener	: POLY HARD TX-F
Mixing ratio	: 100/16 /40 ~ 60 w/w (subject/hardener/thinner)
Application viscosity	: 13 ~ 15 sec (F/cup#4, 20°C)
Pot life	: 4 hrs
Flash off	: 5~10 mins × RT
Curing schedule	: Over 30mins × 75±5°C Object temperature
Disposal	: Do not allow into drains or watercourse

This data sheet represents the actual status of the development and substitutes all previous.

This information is based on tests and research carried out by ANICK.Ltd and was believed to be correct at the time this product sheet was printed but is subject to revision as additional knowledge and experience are gained. Neither ANICK nor any of its subsidiary or associated companies makes any guarantee as to results or otherwise assumes any liability or obligation whatsoever in connection with this information. This product sheet shall not create or form part of any contract between ANICK or any of its subsidiary or associated companies and any other person ; nor is it licence to operate under or intended to enable or induce infringement of any existing patent or other industrial property right.

AkzoNobel Industrial Coatings Korea.,Ltd. 11, Byeolmang-ro 459beon-gil, Danwon-gu, Ansan-si, Kyunggi-do, Korea. 425-833

Tel : +82-31-363-4762, Fax : +82-31-363-4770