

Technical Data Sheet

PP-121 PRIMER BLACK + SENOSOFT SF-10(G) JET BLACK

Page 1/1

created on : 04.July.2013 ; Kim, Chi Won

TECHNICAL INFORMATION		
Name	PP-121 PRIMER BLACK	SENOSOFT SF-10(G) JET BLACK
Color	BLACK	BLACK
Gloss	4.0 ± 0.3 (60° Geometry)	0.9 ± 0.1 (60° Geometry)
Supply viscosity	50.5 ± 4.0 KU (stomer , 20°C)	66 ± 3 KU (stomer , 20°C)
SG wet	0.925 ± 0.05 kg/l	1.06 ± 0.03 kg/l
Weight solids	12.9 ± 2.0 %	51 ± 2 %
Film thickness dry	10 ~ 15 μm DFT	45 ~ 55 μm DFT
Rec. coating system	One coat	Two coat
Shelf life	6 months	6 months

The above data does not represent a specification

APPLICATION TIPS		
Before using	stir well	
Substrate	PPF	A/T#3300#23 PRIMER BLACK
Pre treatment	Cleaning with IPA	
Application method	Air assisted spraying	
Thinner	88-02 Thinner	SF#300 Thiner
Hardener	-	Poly Hard Nc-37
Mixing ratio	100 / - / 40~60	100 / 25 / 25~35
Application viscosity	13.0 ± 1.0 sec (F/cup#4, 20°C)	16.5 ± 1.5 sec (F/cup#4, 20°C)
Pot life	- hrs	4 hrs
Flash off	Wet On Wet	10 min × RT
Curing schedule	: Over 30min × 85±5°C Object temperature	
Disposal	: Do not allow into drains or watercourse	

This data sheet represents the actual status of the development and substitutes all previous.

This information is based on tests and research carried out by ANICK Ltd. and was believed to be correct at the time this product sheet was printed but is subject to revision as additional knowledge and experience are gained. Neither ANICK nor any of its subsidiary or associated companies makes any guarantee as to results or otherwise assumes any liability or obligation whatsoever in connection with this information. This product sheet shall not create or form part of any contract between ANICK or any of its subsidiary or associated companies and any other person ; nor is it licence to operate under or intended to enable or induce infringement of any existing patent or other industrial property right.

AkzoNobel Industrial Coatings Korea.,Ltd. 629-3, Sunggok, Danwon, Ansan, Kyunggi, Korea. 425-833
Tel : +82-31-490-4500, Fax : +82-31-494-6935